

## Product description

Semi matt PVC material for heat transfer applications.

**Thickness** : 105 microns (USA : 4,1 mil) for black and white and 125 microns (USA : 4,9mil) for other colours.

**Carrier** : self-adhesive and transparent polyester.

**Norm** : Oekotex label.

## Suitable for

Cotton, polyester, acrylic and similar fibres.

## Application advises

- 1) Cut the material in reverse with regular flex blade.
- 2) Weed the excess material.
- 3) Heat press the image on the garment with its polyester carrier protected by a silicone paper at 150°C (USA : 300°F) – 10-15 seconds – medium pressure.
- 4) Peel the carrier off when cold.

## Maintenance

Always respect the instructions mentioned on garments.

After heat pressing, wait 24 hours before the first wash.

**Washing** : 90°C (USA : 190°F) max. inside out - without bleach or any aggressive washing products.

**Dried cleaning** : no

**Ironing** : backside

**Storage of the roll** : vertically, one year in a dry room, 15-30°C (USA : 60-85°F), protected from sunlight.

## Caution

Those recommendations are based on our own experiences.

We always recommend making trials before starting standard production.

May 2009

### CHEMICA

8 rue Auguste Poncetton  
42000 Saint-Etienne – France  
Tel : +33.(0)4.77.49.20.90  
Fax : +33.(0)4.77.25.79.82  
[info@chemica.fr](mailto:info@chemica.fr) - [www.chemica.fr](http://www.chemica.fr)

### CHEMICA US

3495 Piedmont Road – Bldg 11, Suite 710  
Atlanta, GA 30305 – USA  
Tel : +1 404.495.5991 – cell +1.404.754.0548  
Fax : +1.404.233.8625  
[rosa.lopes@chemica.fr](mailto:rosa.lopes@chemica.fr) – [www.chemica.fr](http://www.chemica.fr)